Location	Date / Catalog #	Dimensions (approximate)	Pre-conservation condition notes	vacuumed & surface cleaned		wet treatments	-	flattened
Box 1	ND05 FRAGMENTS	N/A	2 large fragments; manuscript text only; discolored, minor scattered stains, edge tears with major losses, breaks along folds	~	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended	~
Box 1	ND06 FRAGMENTS	N/A	numerous small fragments with text from different checklists; discolored, minor scattered stains, tears; grouped together when possible	V	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended	V
Box 1	ND07	N/A	numerous small fragments without text from different checklists; discolored, minor scattered stains, tears	~	N/A	70% ethanol, pH 8.5 calcium hydroxide	lined verso	~
Box 1	1832	16.25" x 20.5"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; tape repairs	~	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	~
Box 1	1848	17" x 21"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V
Box 1	1855	17.25" x 21"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V

Box 1	1857	18" x 21"	off-white ruled paper; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	~
Box 1	1859	18" x 21"	off-white ruled paper; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	/	N/A	7	locally mended	V
Box 1	1864	14" x 22"	tape; 3 postage stamps adhered to recto; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	lined verso; readhere dstamps	~
Box 1	1866	14" x 22"	water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	/	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	<
Box 1	1868	16" x 21	water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	'
Box 1	1869	16" x 21	water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	'
Box 1	1872a	16" x 21	water stains; smeared inks; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V

Box 1	1872b	16" x 21	water stains; smeared inks; purple ink; minor scattered stains, edge tears with minor losses, breaks along folds	~	N/A	No wet treatment (soluble purple ink)	locally mended	•
Box 1	1872c	16" x 21	water stains; smeared inks; purple ink; minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	No wet treatment (soluble purple ink)	locally mended	~
Box 1	1872d	16" x 21	water stains; as above; insect casing present; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	~
Box 1	1873	16 x 21	water stains; smeared inks; purple ink; minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	No wet treatment (soluble purple ink)	locally mended	•
Box 1	1876a	16 x 21	water stains; adhesive resiude; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	~
Box 1	1876b	16 x 21	water stains; large rodent losses; ink spills; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	~	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1876c	16 x 21	liquid stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V

Box 1	1876d	16 x 21	mold stains; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1877	16 x 21	discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1878a	16 x 21	water stains; mold stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	~
Box 1	1878b	16" x 20"	mold damge (black growths and stains); heavy soil deposits; water damage; losses; tears; tape repairs	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V
Box 1	1879	16 x 21	water stains; brown liquid stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V
Box 1	1882	16 x 21	smeared black inks; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V
Box 1	1888 (partial)	12 x 13	reconstructed from fragments; dark and numerous mold stains; water stains; numerous large losses; very weak and deteriorated paper	✓	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended recto & verso	•

Box 1	1890	16 x 25	tapes; stiff; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1893	16 x 25	tapes; stiff; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1896a	14 x 22	culred; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1896b	14 x 22	curled; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	No wet treatment (soluble purple pencil)	locally mended	•
Box 1	1896c	14 x 22	curled; brown liquid stains; tape; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V
Box 1	1897a	14 x 22	curled; brown liquid stains; tape; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	/	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1897b	14 x 22	curled; large edge losses; tapes; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	V	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	V

Box 1	1898	14 x 22	culred; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	•
Box 1	1899	17 x 22	mold damage (black growths and stains); heavy soil deposits; water damage; losses; tears; multiple vertical folds	•	70% ethanol, pH 8.5 calcium hydroxide	locally mended	•