

Unity Voter Checklists
 Job # 14082C
 Itemized Inventory (by date)

Location	Date / Catalog #	Dimensions (approximate)	Pre-conservation condition notes	vacuumed & surface cleaned	removed tape	wet treatments	repaired	flattened
Box 2	1839a	12.5" x 22.25"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; 2 sheets joined with wafer seals	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1839b	13.75" x 25.25"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; tape repairs; water stains	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1840a	13" x 29.5"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; sheets joined with wafer seals; water stains	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1840b	12.75" x 31"	2 sheets; blurred inks; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1840c	13.25 x 26.5"	blue ink; water stains; 2 joined sheets; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	no wet treatment (soluble blue ink)	locally mended	✓
Box 2	1840d	13.25 x 26.5"	ink stains; water stains; 2 joined sheets	✓	N/A	no wet treatment (soluble blue ink)	locally mended	✓

Unity Voter Checklists
 Job # 14082C
 Itemized Inventory (by date)

Box 2	1841	12.25" x 31.25'	2 joined sheets; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1842a	21.5" x 32"	2 joined sheets have separated; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1842b	12" x 32"	found at dump; 2 joined sheets; brown stains; animal waste; numerous tears and losses; heavily soiled	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1843a	13.25" x 32"	pronounced folds (opened during exam); breaking along starch joins (2 sheets)	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1843b	13" x 31.5"	2 joined sheets; pronounced folds (opened during exam); discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1844	20.5" x 31"	3 joined sheets; pronounced folds (opened during exam); discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1847	12.5" x 31.5"	2 joined sheets of blue paper; bird excrement; liquid stains; tape; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water	locally mended	✓

Unity Voter Checklists
 Job # 14082C
 Itemized Inventory (by date)

Box 2	1850	12" x 31"	blue-gray paper; mold damage (growths and stains); tape; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water	locally mended	✓
Box 2	1852	19" x 22"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; large ink spill on front	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1854	19" x 25"	discolored, minor scattered stains, edge tears with minor losses, breaks along folds; large oily stains	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	locally mended	✓
Box 2	1856a	17" x 25"	mold damage (black growths and stains); heavy soil deposits; water damage; losses; tears	✓	N/A	70% ethanol, water, pH 8.5 calcium hydroxide	lined verso	✓
Box 2	1856b	16" x 25"	blue ruled paper; rodent loss; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	N/A	70% ethanol, water	locally mended	✓
Box 2	1860	16.5" x 24"	mold damage (black growths and stains); heavy soil deposits; water damage; losses; tears; tape repairs	✓	with acetone over suction platen	70% ethanol, water, pH 8.5 calcium hydroxide	lined verso	✓
Box 2	1862	16" x 26"	blue laid paper; water stains; minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	70% ethanol, water	locally mended	✓

Unity Voter Checklists
 Job # 14082C
 Itemized Inventory (by date)

Box 2	1884	16 x 25	tapes; stiff; water stains; discolored, minor scattered stains, edge tears with minor losses, breaks along folds	✓	with acetone over suction platen	no wet treatment (soluble blue-gray ink)	locally mended	✓
Box 2	ND01 (c. 1880s) partial checklist	12 x 20	reconstructed from fragments; dark and numerous mold stains; water stains; numerous large losses; very weak and deteriorated paper	✓	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended recto & verso	✓
Box 2	ND02 (c. 1880s) partial checklist	21 x 26	mold damage (black growths and stains); heavy soil deposits; water damage; losses; tears; broken into 6 pieces horizontally; rejoined additional section from fragments	✓	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended recto & verso	✓
Box 2	ND03 (c. 1880s) partial checklist	21 x 26	reconstructed from fragments; dark and numerous mold stains; water stains; numerous large losses; very weak and deteriorated paper	✓	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended recto & verso	✓
Box 2	ND04 (c. 1880s) partial checklist	21 x 26	reconstructed from fragments; dark and numerous mold stains; water stains; numerous large losses; very weak and deteriorated paper	✓	N/A	70% ethanol, pH 8.5 calcium hydroxide	locally mended recto & verso	✓